

Appl. No. 10/601,833
Amendment dated: July 7, 2005
Reply to OA of: April 7, 2005

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

1(currently amended). An optical recording medium comprising:
a) a dielectric layer,
b) a recording layer, and
c) a reflective layer, which are stacked on a surface of a substrate in the described order;

or stacked on said surface in the order of:

- b) the recording layer,
- a) the dielectric layer, and
- c) the reflective layer,

said recording layer comprising $[[a]]$ mixed nickel oxides, wherein said mixed nickel oxide comprises NiO and Ni_2O_3 as a major portion.

2(original). The optical recording medium of claim 1, wherein said mixed nickel oxides decomposes to release a gas upon heating.

3(original). The optical recording medium of claim 1, wherein said mixed nickel oxides in said recording layer becomes transparent from its original black color upon heating.

4(original). The optical recording medium of claim 2, wherein said heating is at a temperature of 150 to 370°C.

5(original). The optical recording medium of claim 3, wherein said heating is at a temperature of 150 to 370°C.

Appl. No. 10/601,833
Amendment dated: July 7, 2005
Reply to OA of: April 7, 2005

6(original). The optical recording medium of claim 1, wherein said dielectric layer comprises silicon oxide or Al_2O_3 .

7(original). The optical recording medium of claim 1, wherein said reflective layer is comprised of a member selected from the group consisting of Ag, Al, Au, Pt, Cu and an alloy thereof.

8(original). The optical recording medium of claim 1, wherein said recording layer is formed by a reactive sputtering technique.

9(original). The optical recording medium claim 8, wherein said recording layer is formed by reactive sputtering in an oxygen gas containing atmosphere using NiO as a target.

10(original). The optical recording medium of claim 1, wherein said recording layer is 30-100 nm in thickness.

11(original). The optical recording medium of claim 1, wherein said dielectric layer is 10-300 nm in thickness.

12(original). The optical recording medium of claim 1, wherein said reflective layer is 80-130 nm in thickness.

13(new). The optical recording medium of claim 1, wherein said mixed nickel oxide consist essentially of NiO and Ni_2O_3 .

14(new). The optical recording medium of claim 1, wherein said mixed nickel oxides consists of NiO and Ni_2O_3 .